


Curekind TBBS(NS)

DESCRIPTION	 N-tert-butyl-2-benzothiazole Sulfenamide	Specification	
		Powder	Granule
	Appearance	Grey-white Powder(Granule)	
	Initial Melting Point, °C min.	104.0	104.0
	Heat Loss, % max.	0.40	0.40
	Ash, %	0.30	0.30
	Density, g/cm ³	1.30	1.30
	Residue on 150µm, % max.	0.10	-
	Residue on 63µm, % max.	0.50	-

Characteristics Curekind® TBBS is grey-white powder, soluble in benzene, chloroform, carbon disulfide, acetone, methanol, alcohol, difficultly soluble in gasoline, insoluble in water, dilute acid and dilute alkali solution.

Application Curekind® TBBS is a delayed action vulcanization accelerator for natural and synthetic rubber. The vulcanizing speed is similar to CBS, but it's delaying is larger than CBS. Little pollution and not changed color. Can be used on rubber tires etc rubber products.

Safety and Toxic Refer to the MSDS

Storage Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastics film bag. Net weight 25kg per bag. Net 500kg per pallet.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.

CURELIND®TBBS(NS) TECHNICAL DATA SHEET (TDS) version 1.3

Ningbo Actmix Rubber Chemicals Co., Ltd.

TEL:+86-574-81880068 FAX:+86-574-88002102 Email: actmix@actmix.cn [Http://www.actmix.cn](http://www.actmix.cn)