


# Curekind ZDTP

DESCRIPTION	 <p>(R = alkyl)</p> <p>Zinc dialkyldithiophosphate</p>	Items	Specification	
		Appearance	Liquid	Amber liquid
		Sulfur, %	14.0-18.0	
		Heat loss, %	Max.0.06	
		25°C Density (g/cm <sup>3</sup> )	1.05-1.15	

**Characteristics** Curekind® ZDTP, a fast curing secondary accelerator for NR and EPDM.

**Application** Curekind®ZDTP mainly used as curing accelerator for EPDM, non-blooming, lower cost and fast curing rate. Because of non-amine based structure, Curekind®ZDTP can be used to Non-nitrosamine formed curing systems. Curekind®ZDTP is regulated for use in articles in contact with food as specified under BgVV.XXI, category 4, and is not regulated for use in FDA food contact applications.

**Safety and Toxic** Refer to the MSDS

**Storage** Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

**Package** N.W.200Kg/drum..

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.