


ACTMIX TCY-70GEO F140

Vulcanizator TCY

A C T I V E M A T E R I A L	 <p>Trithiocyanuric acid C₃H₃N₃S₃ M.W.: 177.27 CAS: 638-16-4 EINECS: 211-322-8</p>	PROPERTIES: TCY is an effective vulcanizator for halogen-containing rubber such as CO, ECO, CIIR, BIIR and ACM and is a co-vulcanizator for NBR/PVC blending elastomer. Pre-dispersed anti-scorcher CTP-80 can be added in the formula to improve storage stability of TCY rubber compounds due to its inclination to scorching. Moreover, TCY can improve adhesion of rubber and metal.	DOSAGE: For ACM: 0.7-2.1phr with 0.6-1.9 phr ZDBC, 1.2phr CTP and 2.5-3.5phr sulfur; For ECO: 0.7-1.4phr with 1.2phr CTP and 4phr MgO; For CIIR, BIIR: 1.4-2.9phr with 0.4-0.7phr MgO; For NBR/PVC: 1.4-2.9phr with 1-2phr DBD.
		TYPICAL VALUES: Melting point: 320°C (decomposed) Purity: Min 97% Ash content: Max 0.3% Heating loss content: Max 0.5% 63µm sieve residue: Max 0.5%	

M A S T E R B A T C H	PRODUCT Active Content (%) Appearance Filtration (µm) Binder Sulfur Content (%) Density (g/cm ³)	Actmix TCY-70GEO F140 70 Yellow Granules 140 ECO 37.5 1.45
	* Binder type can be customized. Except ECO, others binders, such as SBR, NBR, AR also can be available for.	
	SAFETY&TOXICITY: Please refer to related SDS.	
	PACKAGING&STORAGE: Net weight 25kg/PE bags lined carton; Net weight 600 kg/pallet. Shelf-life: 1 year in its original packaging Stored in a dry and cool place.	

Compared to traditional TCY powders, Actmix TCY-70GEO F140 allows:

- Dust free products with a complete filtration up to 100µm, no skin sensitization, health guard of operators.
- Effective guarantee of activity of TCY with 8µm mean size due to pre-dispersed masterbatch.
- Tack free products at room temperature, convenience and accuracy on ingredients.
- Lower Mooney viscosity at lower temperature (50°C), higher quality of dispersion.
- Impurity free, blocked filter free of extrusive products, scrap rate reduction and higher productivity thanks to filtration.
- Wider compatibility with other elastomers.

G: granule, P: plate, E: EPDM binder, N: NBR binder, S: SBR binder, A: ACM binder, EO: ECO binder, F140: filtration and micron number of filter
 The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.